



**NATIONAL TESTING STANDARDS INC.**  
RESEARCH AND TESTING LABORATORIES

Report No. 29952-2

December 17, 2008

Client: Jensen Swing Products, Inc.  
9327 Wheatlands Rd.  
Santee, CA 92071

Reference: Charvet Vecchio  
Letter of 11/05/08

Subject: Lead Content of Plates & Triangles.

**Sample Description:**

One sheet of stamped metal was submitted by the Client and identified as a steel swing insert.

**Request:**

Analyze the submitted insert and identify the type of steel.

**Method:**

The submitted metal sheet was analyzed by standard emission spectrographic procedures.

**Results:**

<u>Element</u>	<u>Value (%)</u>
C	0.47
Mn	0.67
P	0.011
S	0.009
Si	0.23
Cu	0.02
Ni	0.01
Cr	0.08
Mo	0.02
Fe	remainder

Continued. . .

**NATIONAL TESTING STANDARDS INC.**

Report No. 29952-2

December 17, 2008

Page 2

Client: Jensen Swing Products, Inc.

Conclusion:


This analysis corresponds to an alloy type 1045.

Comments:

The carbon content of alloy 1045 is 35% to 40 % lower than the carbon content for alloy 1075.

This difference is significant for certain physical properties such as tensile strength, tear resistance and hardness.

NATIONAL TESTING STANDARDS

  
by Lewis F. West