



**NATIONAL TESTING STANDARDS INC.**  
**RESEARCH AND TESTING LABORATORIES**

Report No. 29952-2

December 17, 2008

Client: Jensen Swing Products, Inc.  
 9327 Wheatlands Rd.  
 Santee, CA 92071

Reference: Charvet Vecchio  
 Letter of 11/05/08

Subject: Lead Content of Plates & Triangles.

**Sample Description:**

One sheet of stamped metal was submitted by the Client and identified as a steel swing insert.

**Request:**

Analyze the submitted insert and identify the type of steel.

**Method:**

The submitted metal sheet was analyzed by standard emission spectrographic procedures.

**Results:**

<u>Element</u>	<u>Value (%)</u>
C	0.47
Mn	0.67
P	0.011
S	0.009
Si	0.23
Cu	0.02
Ni	0.01
Cr	0.08
Mo	0.02
Fe	remainder

Continued . . .

**NATIONAL TESTING STANDARDS INC.**

**Report No. 29952-2**

December 17, 2008

Page 2

**Client:** Jensen Swing Products, Inc.

**Conclusion:**


This analysis corresponds to an alloy type 1045.

**Comments:**

The carbon content of alloy 1045 is 35% to 40 % lower than the carbon content for alloy 1075.

This difference is significant for certain physical properties such as tensile strength, tear resistance and hardness.

**NATIONAL TESTING STANDARDS**

  
by Lewis F. West